PIPE SEAMLESS BLACK SCHEDULE 80 ASTM 106 GR.B/API 5L

ASTM A 106 GR.B Standard

Chemical Composition:

C:0.3% max Mn:0.29-1.06% P:0.035%max S:0.035%max Si:0.1%min Ni:0.4%max
Cr: 0.4%max Cu:0.4%max Mo:0.15%max V:0.08%max

Mechanical properties:

Tensile strength:≥415MPa

Yield strength≥240MPa

Elongation≥ 22%

Delivery status:Hot rolled